

Product information

Sasolwax 0716

printed on: 22.09.2016

Revision: 12.04.2016

| Property | Specification | Unit | Method |
|--------------------------|----------------------|-------------|---------------|
| Congealing point | 56,0 .. 60,0 | °C | ASTM D938 |
| Oil content | 0,00 .. 0,80 | % | ASTM D721 |
| Needle penetration 25 °C | 14 .. 20 | 1/10mm | ASTM D1321 |
| Colour Saybolt | 29 .. 30 | | ASTM D156 |
| Reqs RAL/ Blend | Complies | | RAL-GZ 041 |

This information is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including any existing third party patent rights. In particular, no guarantee of properties in the legal sense is implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not exempted from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names used by other companies is neither a recommendation, nor is it intended to suggest that similar products could not be used. All our business transactions shall be governed exclusively by our General Sales Conditions.

Sasol Wax GmbH

Gesellschaft mit beschränkter Haftung, Location Hamburg, Germany, Registration No. Hamburg HRB 73963

Managing Director: Edwin Vorsteveld

VAT-No. DE 118 922 039 parent company Sasol Wax Int. AG Tax No. 27/164/00088

www.sasolwax.com wax@de.sasol.com